

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 090 380
A1

EUROPEAN PATENT APPLICATION

(21) Application number: 83103001.0

(51) Int. Cl.³: **B 29 D 7/24, B 32 B 27/08**

(22) Date of filing: 25.03.83

(30) Priority: 26.03.82 DK 1398/82

(71) Applicant: Rasmussen, Ole-Bendt, Forchwaldstrasse 23,
CH-6318 Walchwil/Zug (CH)

(33) Date of publication of application: 05.10.83
Bulletin 83/40

(72) Inventor: Rasmussen, Ole-Bendt, Forchwaldstrasse 23,
CH-6318 Walchwil/Zug (CH)

(34) Designated Contracting States: AT BE CH DE FR GB IT
LI LU NL SE

(74) Representative: Berg, Wilhelm, Dr. et al, Dr. Wilhelm
Berg, Dipl.-Ing. Otto F. Stepf Dipl.-Ing. Hans-Georg
Schwabe Dr. Dr. Kurt Sandmair, Patent Attorneys
Mauerkircherstrasse 45, D-8000 Munich 80 (DE)

(53) Method and apparatus for preparing a high strength sheet material.

(57) A method of preparing a high strength sheet material comprising (a) forming a laminate comprising at least two layers of a thermoplastic polymer material, each layer having a fibrillar grain structure providing a predominant direction of splittability in each said layer, and wherein the layers are bonded to one another with the said predominant directions of splittability transverse to each other, (b) biaxially orienting the molecules of said layers by stretching the layers in substantially uniaxial steps, the transverse stretching being effected by applying pressure to the surface of the laminate along lines extending substantially in the longitudinal direction of the laminate to impart thereto a waved configuration, and (c) subjecting the biaxially oriented laminate to a heat treatment while allowing at least 7% shrinkage of the laminate to take place in at least its transverse direction.

Method and apparatus for preparing a high strength sheet material

This invention relates to a method of preparing a high strength sheet material comprising forming a laminate comprising at least two layers of a thermoplastic polymer material, each layer having a fibrillar grain structure providing a predominant direction of splittability in said layer, the layers being bonded to one another with the said predominant directions of splittability transverse to each other, and biaxially orienting the molecules of said layers by stretching the layers in substantially uniaxial steps, the transverse stretching being effected by applying pressure to the surface of the laminate along lines extending substantially in the longitudinal direction of the laminate to impart thereto a waved configuration.

British patent specification No. 1.526.722 describes the manufacture of a laminate by a method comprising extruding at least two layers, each consisting of a blend of polymers which are incompatible to such a degree that the blend on solidification forms a dispersion of particles of one polymer in a polymeric matrix melt, attenuating each layer to obtain a fibrillar grain structure having a predominant direction of splittability after solidification into a film, bonding the two layers to one another with the said predominant directions transverse to one another and biaxially stretching the solidified laminate in substantially uniaxial steps, the stretching being conducted at a temperature sufficiently low to maintain the predominant direction of splittability in each layer.

The specification of British patent No. 1.526.724 describes the manufacture of a laminate comprising at least two films of a polymeric material by a method which comprises pressing the film together along lines extending substantially in the longitudinal direction of the films and simultaneously stretching the films in the transverse direction, thereby forming a laminate having a waved configuration in its transverse direction.

The latter method may advantageously be utilized to bond the two layers together and to effect the transverse stretching of the laminate in the method described in the British patent specification No. 1.526.722. However, the laminates thus produced ordinarily exhibit longitudinal striations which impart to the laminate thickness variations in the transverse direction and consequently an unsatisfactory rigidity, low temperature tear strength and sealability.

The object of the invention is to provide a laminate having

an improved rigidity, an improved low temperature tear strength and improved sealability.

Another object of the invention is to provide a laminate which is suitable for use in the manufacture of heavy duty sacks, e.g. sacks for Portland cement.

A further object of the invention is to provide a laminate having an increased yield point and improved anti-creep properties.

These objects and other objects which will become clear from the following description are obtained by the invention.

According to a first aspect of the invention there is provided a method of the above mentioned type which method comprises the additional step of subjecting the biaxially oriented laminate to a heat treatment while allowing at least 7% shrinkage of the laminate to take place in at least its transverse direction.

This aspect of the invention is based on the discovery that the relatively thin zones of the transversely stretched laminates are overstretched and that the material in these zones exhibit a pronounced tendency to contract when heated to an elevated temperature. Consequently, variations in the thickness of the laminate tend to be reduced or almost eliminated during such a heat treatment.

It is preferred to effect a shrinkage of at least 12% in the transverse direction.

The heat treatment may be effected in an oven but in practice it is preferably effected by contacting the laminate with the surface of a heated body because the transverse contraction of the laminate will then occur under more controlled conditions. The heated body is preferably a heated roller.

In order to reduce the friction between the laminate under contraction and the heated roller and thus permit that the transverse contraction becomes almost fully even over the width of the laminate, the heat treatment is advantageously effected by contacting a longitudinally pleated laminate with said heated roller. It should be mentioned that a transverse contraction of the laminate may take place after it has left the heated roller but the spontaneous tendency to contract is most pronounced at the start of the heat treatment, i.e. while the laminate is in contact with the heated roller.

If the transversely stretched waved laminate is allowed to expand due to its inherent elastic recovery properties before it is subjected to the heat treatment, irregular pleats may be formed and

consequently the thermally induced transverse contraction also becomes irregular. Therefore, it is preferred to introduce the laminate onto the heated roller while it still has the waved configuration obtained during the last transverse stretching step. The laminate preferably is
5 allowed to contract longitudinally during said last transverse stretching step. This effect is achieved by keeping a low tension while feeding the laminate into the last transverse stretching device (usually a pair of grooved rollers).

This longitudinal contraction improves puncture and tear
10 strength and further improves the form stability of the final product.

When the means for transversely stretching the laminate comprise at least one pair of intermeshing grooved rollers, one or more conveyor rollers are preferably arranged between the last pair of intermeshing grooved rollers and the said heated roller, the adjacent rollers in said assembly being in so close proximity to one another that the film is supported by a roller surface during substantially all of its travel from the last pair of grooved rollers to the heated roller.
15

The transverse contraction should preferably be combined
20 with a longitudinal contraction and said longitudinal contraction should be as complete as possible at the annealing temperature used. Therefore, the longitudinal tension in the laminate should preferably be adjusted to a minimum at its introduction onto the hot roller and at the take-off from the hot roller or rollers.

However, when a pleated laminate contacts the hot roller
25 under low tension, air bubbles may be entrapped between said laminate and the roller surface and such air bubbles may lead to an uneven shrinkage.

In a preferred embodiment of the method of the invention
30 such entrapped air bubbles are removed by squeezing while allowing the laminate to slide along the surface of the hot roller. This can be achieved in a simple manner by lightly pressing, e.g. by means of a counter roller, the laminate against the surface of the hot roller. More efficiently, however, the entrapped air bubbles are removed by
35 subjecting the laminate to vibrations comprising short intervals during which the laminate is forced against the surface of the hot roller, e.g. by means of a counter roller which is oscillating relative to the hot roller.

The counter roller is preferably one of the above mentioned

transfer rollers.

A second aspect of the invention relates to a particularly advantageous combination of material composition, stretching conditions and a heat treatment.

5 The method according to this aspect comprises forming a laminate comprising at least two layers of a thermoplastic polymer material, each layer having a fibrillar grain structure providing a predominant direction of splittability in each of said layers, the layers being bonded to one another with the said predominant directions of
10 splittability transverse to each other, and biaxially orienting the molecules of said layers by stretching the layers in substantially uniaxial steps, wherein the thermoplastic polymer material consists of a blend of 40-85% by weight of polypropylene and 60-15% by weight of a lower melting or amorphous admixture which a) mainly consists of
15 polyethylene incl. copolymers thereof, b) exhibits substantially the same or a higher elongation at break than the said polypropylene when tested at room temperature under slow stretching, c) has a modulus of elasticity which at room temperature is equal to or lower than that of a blend of 90% polyethylene of a density of 0.95 and 10%
20 EPR containing 25% ethylene and 75% propylene, wherein at least the last 25% of the biaxial stretching, measured on the area increase, is carried out below 50°C, and wherein the biaxially oriented laminate is subsequently heat treated at a temperature higher than 50°C, preferably at least 70°C.

25 By the extrusion of the base films for the laminate, the polypropylene will crystallize (as established by electron microscopy) in the form of fibrils having a diameter of from about 0.05 to 2 microns, while the softer polymeric admixture will form a coat on and embedment for these stiffer fibrils. It is well known that polypropylene
30 begins to recrystallize at 50-60°C, whereby the stiffness of the fibrils generally increases. In the combination defined above this stiffening is highly advantageous.

 The feature that biaxial stretching (or at least the last part thereof) is carried out at a lower temperature even though the stiffening of the fibrils is desirable, might appear to be an unnecessary
35 complication, but in actual fact this sequence of steps has been found to be very advantageous.

 Similar to what is described in connection with the first aspect of the invention, the heat treatment should preferably be car-

ried out under such conditions that at least 7% shrinkage of the laminate takes place in at least its transverse direction, and it should generally be aimed at a higher shrinkage, such as 12% or more.

5 The use of the special transverse stretching method described as the first aspect of the invention is also advantageous.

Similar to what is well known from high-strength cross-laminates made from uniaxially oriented films, the molecular weight is important as far as the strength is concerned, and generally the melt flow index of the polypropylene should not exceed 1 according to
10 ASTM D 1238 condition L. However, if the molecular weight distribution is particularly even, melt indices up to about 3-4 can be used with good result.

The stretch ratio should preferably not exceed 2.5:1 in any direction, and the optimum ratio is usually between 1.3-1.9, depending
15 on the final use of the laminate. These values refer to the state when shrinkage has taken place (if shrinkage has been effected).

In a preferred embodiment of this second aspect of the invention the admixture comprises as its major component linear polyethylene. While for instance a highly branched polyethylene is less
20 suitable, i.e. due to the fact that its elongation at break at room temperature is substantially lower than that of polypropylene, it has been found that the use of linear polyethylene in such admixture cooperates synergistically with the embedded fibrils of polypropylene (in the stretched and heat treated condition, as defined) to provide
25 particularly advantageous mechanical properties. Furthermore, it has been found that the low stiffening temperature of polyethylene improves the low temperature performance of the laminate to a surprising extent, such that the very pronounced stiffening of polypropylene at temperatures below about 0°C in this case generally becomes an
30 advantage rather than a disadvantage for the mechanical properties of the laminate. In this connection it is important that the admixture which remains soft at the low temperatures is not occluded but on the contrary forms embedment for the stiff polypropylene fibrils.

The linear polyethylene in this embodiment of the invention
35 preferably is high density polyethylene of a melt index according to ASTM D 1238 condition L not exceeding 0.2 and the admixture further comprises a softening component, preferably an elastomer.

Alternatively, the linear polyethylene can be low density linear polyethylene. Generally, its melt flow index (ASTM D 1238,

condition E) should not exceed 5, and much lower melt flow indices are preferable.

5 High molecular weight linear low density polyethylene, i.e. of a melt index not exceeding 0.2 (ASTM D 1238 condition L) is particularly advantageous.

The designation "lineary low density polyethylene" or "LLDPE" refers to polyethylene which is branched in controlled manner to achieve a high elongation at break. This controlled branching, as known, can be established, either by a high-pressure polymeriza-
10 tion by using a suitable catalyst, or by copolymerization with a suitable branch-forming monomer, such as butene, pentene, hexene or octene, of which the latter is preferable in connection with the present invention.

Advantageously, the polyethylene is selected so that its
15 shrinkability at 100°C, in the oriented state, is higher than the corresponding shrinkability of the polypropylene.

Under these circumstances, a special morphology will result. This morphology is characterized by twists or waves on the polypropylene fibrils with a twist or wave length of the order of 1 micron
20 which can be observed in a scanning electron microscope.

The mechanical state of this structure has some similarity with cement which is reinforced with prestretched iron.

A third aspect of the invention relates to the manufacture of a laminate having properties which make the material particularly
25 useful for the manufacture of heavy duty sacks.

The method according to this aspect comprises forming a laminate comprising at least two layers of a thermoplastic polymer material, each layer having a fibrillar grain providing a predominant direction of splittability in each said layer, the layers being bonded
30 to one another with the said predominant directions of splittability transverse to each other, and biaxially orienting the molecules of said layers by stretching the layers in substantially uniaxial steps, and the method is characterized in that the direction of splittability of each layer of said layers of the laminate to be biaxially oriented forms
35 an angle of between 10 and 35°C with the machine direction of the laminate.

A sack usually has a width which is much smaller than its length and has been made in such a manner that the machine direction of the thermoplastic film becomes the length direction of the sack.

During filling of the sack and regular handling of the filled sack, the most important performance factor is the yield point in its longitudinal direction. In case the filled sack is dropped, the most important performance factors are tear propagation strength, puncture strength and impact strength, the latter under forces which mainly act in the transverse direction of the sack.

It might be assumed that a laminate in which the direction of splittability of each layer is lying relatively close to the machine direction would be weak because a rupture (formed by puncturing or snagging) might easily propagate under the influence of these transversely acting forces.

The fact, however, is that the opposite is true, namely that the laminate thus produced generally exhibits an advantageous tear propagation resistance in all directions, particularly in the directions which form an angle of 45° to the machine direction. The tear propagation resistance in the said directions has been found determining for the strength of a stitched seam in cross laminated film material, such as a sewn sack.

An additional advantage obtained relates to the formation of heat seals in the manufacture and/or closing of the sack.

While the laminate can readily be formed into a tube with a glued or heat-sealed longitudinal seam having overlapping edges and a relatively low peel strength is sufficiently in such type of seam, it is complicated and expensive to fold the material to form overlapping edges at the bottom and/or at the top of the sack. Consequently, there is an important practical need for a high-strength film which readily can be heat-sealed to itself to form seams across its machine direction with a resulting high peel strength.

One measure in this connection is the choice of a suitable surface layer on the laminate.

Another measure is the allowance of a substantial contraction of the laminate perpendicular to the seam that is parallel to the length of the sack, so that the increased thickness can compensate for the loss of molecular orientation caused by the heat-sealing. At the same time it is essential to limit the contraction of the laminate parallel to the direction of the seam which is perpendicular to the length of the sack.

It has now been found that the melt orientation of the molecules produced in connection with the extrusion (as distinguished

from the subsequent biaxial orientation at a much lower temperature) plays a very important role for the contraction during heat sealing, and that consequently the use of relatively small angles between the machine direction and the directions of splittability (substantially
5 coinciding with the direction of melt orientation) leads to substantially improved heat seals at the top and/or the bottom of the sack, in particular with respect to the impact actions when a filled sack is dropped.

In this third aspect of the invention a heat treatment subsequent to the biaxial stretching is also highly preferable and similar
10 to what is described in connection with the first aspect of the invention, the heat treatment should preferably be carried out under such conditions that at least 7% shrinkage of the laminate takes place in at least its transverse direction and it should generally be aimed at a
15 higher shrinkage, such as 12% or more.

The use of the special transverse stretching method in connection with the first aspect of the invention is also advantageous. The stretch ratio should preferably not exceed 2.5:1 in any direction and the optimum ratio is usually between 1.3-1.9, depending on the
20 final use of the laminate. These values refer to the state when shrinkage has taken place (if shrinkage has been effected).

In the practice of this third aspect of the invention, the choice of polymers and heat treatment which are disclosed above in connection with the second aspect of the invention are also advantageously used.
25

Furthermore, this third aspect may advantageously be used in connection with the production of laminates produced in accordance with claims 22 and 23 of the above mentioned British patent specification No. 1.526.722. According to these claims one unoriented two-ply
30 laminate in which the layers exhibit criss-crossing directions of splittability is produced directly by coextrusion, using rotating die-parts. It has now been found that the properties of the final biaxially oriented laminate produced on the basis of this coextrusion method is substantially improved when the angles between the directions of
35 splittability of each layer and the machine direction fall within the range 10° - 35° .

A fourth aspect of the invention relates to an advantageous material composition which in particular exhibits a high low temperature performance and which is readily stabilized against ultra-violet

light.

The method according to this fourth aspect of the invention comprises forming a laminate comprising at least two layers of a thermoplastic polymer blend comprising polyethylene, each layer
5 having a fibrillar grain structure providing a predominant direction of splittability in each said layer, the layers being bonded to one another with the said predominant directions of splittability transverse to each other, and biaxially orienting the molecules of said layers by stretching the layers in substantially uniaxial steps to convert the
10 grain of polymer into a zig-zagging micropattern, said blend being composed of high molecular weight high density polyethylene and low density polyethylene having significantly lower molecular weight, said low density polyethylene being selected from the group of copolymers and/or branched polyethylenes which a) exhibit substantially the same
15 or higher elongation at break than the said high molecular weight high density polyethylene when tested at room temperature under slow stretching, b) are capable of distinctly segregating, while forming a distinct microphase, from said high molecular weight high density polyethylene on cooling of a molten homogeneous blend of the said
20 components.

The term "High molecular weight high density polyethylene" ("HMHDPE") comprises HDPE having a melt flow index of about or lower than 0.2 according to ASTM D 1238, condition E.

As regards the low density polyethylene, it may advantageously be LLDPE (see explanation of this term above).
25

By the combination of polymers which chemically are so closely related and blend homogeneously in the melt but still, i.a. due to the different molecular weights, clearly segregate from each other on cooling, one obtains a particularly fine and regular grain of polymer consisting of highly crystalline and relatively stiff microfibrils in a less crystalline and softer matrix. This structure has been observed
30 in an electron microscope after selectively dissolving the matrix material. As mentioned above the grain thus produced was particularly regular and the distance between adjacent fibrils (from centre to centre) was in the order of magnitude $1/10.000$ mm ($1/10$ μ m). The regular and fine structure, and the good bonding between the stiffer fibrils and softer matrix is of importance as far as the strength properties are concerned. The crystalline nature of the soft matrix gives the material low tendency to cold-flow.
35

The blending ratio between the HMHDPE and the LDPE (preferably LLDPE) may conveniently be in the range of from 25:75 to 75:25.

5 HMHDPE exhibits a high tendency to molecular melt orientation. Such melt orientation (except when weak) generally has been found a drawback in connection with the present invention. In this connection one must distinguish between the morphological "orientation" (grain of polymer) which is essential in the present invention, and the molecular melt orientation, which i.a. reduces the elongation
10 of break and thereby the energy absorption.

Therefore, it is advisable to use low air cooling at the exit of the extruder so that the molecular melt orientation can be practically minimized.

15 Further improvements in this respect, and other essential improvements, can be obtained when the blend further contains polypropylene of a molecular weight significantly lower than said high molecular weight high density polyethylene.

During draw-down at the exit from the extrusion die the HMHDPE will be molecularly oriented and will thereby "carry" the
20 film, so that the polypropylene is protected against any strong molecular orientation, and after crystallization of the polypropylene the latter will "carry" the film so that the HMHDPE has the opportunity to loose part of its molecular orientation again.

The ratio in the blend between the polypropylene and the
25 HMHDPE + LDPE can conveniently be in the range of between 0 and 70/30.

The blend may further contain minor amounts of an alloying agent, e.g. a copolymer of propylene and a polyolefin with 4 or more carbon atoms.

30 Similar to what is stated above in connection with the second and third aspect of the invention, the sheet is preferably allowed to shrink at least 7% in at least one direction, and the stretch ratio in any direction and determined after shrinkage preferably does not exceed 2.5:1.

35 High-strength laminates manufactured according to this fourth aspect of the invention can conveniently be made with the angles and other features described under the third aspect.

Finally, a fifth aspect of the invention concerns the conservation of the correct amount and kind of bonding between the cross-

laminated films, even after a strong heat-treatment.

5 The method according to the fifth aspect comprises forming a laminate from at least two separately extruded films of thermoplastic polymer material, each film comprising a) a main layer exhibiting a
fibrillar grain structure providing a predominant direction of splittability in each said film, and b) a second layer for controlling bonding
10 strength, the films being bonded to one another with the said predominant directions of splittability transverse to each other, the second layer of one film facing the second layer of the other film, and biaxially orienting the molecules of said layers by stretching the layers in
substantially uniaxial steps, the transverse stretching and the bonding being effected by applying pressure to the surface of the laminate
15 along lines extending substantially in the longitudinal direction of the laminate to impart thereto a waved configuration, and in which main layers the fibrillar grain structure consists of highly crystalline polypropylene and/or high density polyethylene micro fibrils which
are generally embedded in a matrix material predominantly consisting of low density polyethylene, and preferably a) said matrix material
20 exhibits an elongation at break similar to or higher than that of the fibrilforming polypropylene or high density polyethylene when tested at room temperature under slow stretch, and b) said second layers
mainly consist of branched polyethylene and exhibit a heat-seal temperature higher than 100°C and an elongation at break similar to or
higher than that of fibrilforming polypropylene or high density polyethylene.
25

The branched polyethylene for the second layer preferably is LLDPE, to which there should usually be added about 35% or less of an elastomer, such as ethylene-propylene rubber. The matrix material may also conveniently be based on LLDPE.

30 When the laminate so produced is heated up to about 100°C - either by a regular heat treatment as described e.g. under the first aspect of this invention, or because hot goods (e.g. hot cement) is packed in the laminate or in sacks made therefrom, the bonding strength will be maintained at the correct, not too high level, which
35 is essential for the achievement of a high tear-propagation resistance.

It is preferred to heat treat the laminate below the temperature at which the second layers heat-seal to each other. The matrix material used preferably has a melting range lower than that of said second layer and the laminate is allowed to shrink, at least in one di-

rection, during said heat treatment.

The extruded films from which the laminate is produced may further comprise a surface layer which facilitates sealing of the laminate. The said layer can with advantage consist of plain or almost
5 plain lineary low density polyethylene.

The invention also relates to an apparatus for carrying out the method according to the first aspect of the invention. The apparatus of the invention comprises means for preparing a laminate and means for stretching said laminate in substantially uniaxial steps, the
10 means for transversely stretching the laminate comprising means for applying pressure to the surface of the laminate along lines extending substantially in the longitudinal direction of the laminate to impart thereto a waved configuration, and the characteristic feature of said apparatus is that it further comprises means for heat treating the bi-
15 axially oriented laminate while allowing a shrinkage of the laminate to take place in at least its transverse direction.

The means for preparing the laminate are preferably those described in British patent specification No. 1.526.722 and the means for transversely stretching the laminate are preferably those disclosed
20 in British patent specification No. 1.526.724.

As mentioned above the heating means preferably consist of a heated roller and the apparatus of the invention preferably comprises means for introducing the laminate onto said heated roller in a longitudinally pleated configuration.

The latter means may be a separate pleating device but in
25 case a waved configuration has been imparted to the laminate by means of a pair of intermeshing grooved rollers of the type described in British patent specification No. 1.526.724, it is preferred to place the heated roller in close proximity of the surface of one of the
30 rollers of said pair of intermeshing grooved rollers to allow the laminate to be contacted with the surface of said heated roller immediately after having left the surface of said roller of the pair of intermeshing grooved rollers.

In this manner the fine waved configuration of the laminate
35 is maintained during its travel from the pair of intermeshing rollers to the heated roller and the contracted laminate resulting from the following heat treatment exhibits very useful strength properties.

In an apparatus in which the means for transversely stretching the laminate comprise at least one pair of intermeshing

grooved rollers, one or more conveyor rollers are preferably arranged between the last pair of intermeshing grooved rollers and the said heated roller, the adjacent rollers in said assembly being in so close proximity to one another that the film is supported by a roller surface during substantially all of its travel from the last pair of grooved rollers to the heated roller.

The invention will be further described with reference to Fig. 1 of the drawings which schematically illustrates an apparatus for effecting the transverse stretching and heat treatment steps of the method of the invention.

Fig. 1 illustrates a roll 1 of a laminate 2, and 3 is a set of grooved rollers. The set of grooved rollers 3 are mounted adjacent to an oscillating roller 4 mounted so close to a hot roller 5 that the laminate 2 is pressed against the surface of the hot roller 5 during short intervals. A cooling roller 6 is also mounted adjacent to the heated roller. The apparatus further comprises a set of take-off rollers 7 and a roll 8 of transversely stretched and heat treated laminate 9.

The operation of the apparatus illustrated is as follows:

Laminate 2 is unwound from the roll 1 and is passed through the nip of the set of grooved rollers 3 in which the laminate is stretched in its transverse direction so as to impart thereto a waved configuration. Following the transverse stretching the laminate is contacted with the oscillating roller 4 and subsequently contacted with the hot roller 5. Due to the oscillating movement of the roller 4 relative to the hot roller 5 the heated laminate is free to shrink longitudinally. After leaving the hot roller 5 the laminate is cooled on cooling roller 6 and is subsequently wound so as to form a roll 8 after having passed through the nip of the set of take-off rollers 7.

The invention will now be described in further detail with reference to the following examples.

EXAMPLE 1

A series of 3-layered tubular films are extruded. Each film has a main layer in the middle, a layer for improved heat sealing on one surface and a layer for improved lamination on the other surface. The three layers form 75%, 15% and 10%, respectively, of the total film.

The main layer consists of a blend (intimately pre-blended in a planetary screw extruder) of

1) a so-called "block-copolymer" of propylene and ethylene

sold under the trade name "Hostalen 1022",

2) an ethylene-propylene rubber sold under the trade name "Nordel 1500",

3) a high molecular weight high density polyethylene sold under the trade name "Hostalen 9255 F".

5

Component 1 has melt flow index of 0.4 according to ASTM D 1238 condition L and analysis shows that it contains about 80% homo-polypropylene, about 10% polyethylene and about 10% ethylene-propylene rubber. A true block-copolymer is hardly detectable by the analysis, but it is very likely that there are undetectable segments of polyethylene on the polypropylene which segments assist in forming a good polymer-in-polymer dispersion.

10

Component 2 contains about 20% ethylene and exhibits some ethylene crystallinity and a melt index of about 0.3 measured at 190°C but otherwise under the same conditions as in the above mentioned ASTM specification (i.e. at "condition E" instead of "condition L").

15

Component 3 has a density about 0,95 and melt index of about 0.05 measured under the same conditions as component 2.

The blending ratios appear from the following table 1:

20

25

30

35

TABLE 1

SAMPLE	CODE AND REMARKS	PP-COPOLYMER		EPR ADMIXED	TRUE EPR	HMM HDPE ADMIXED	TRUE PE	FINAL STRETCH RATIO (AFTER SHRINKAGE, IF SHRUNK)		ANNEALING TEMPERATURE °C	SHRINK RATIO %	
		%	%					P/D	C/D		P/D	C/D
a.	245,174	90	72	10	19	0	9	1.50:1	1.50:1	(35)		
b.	245,80	90	72	10	19	0	9	1.38:1	1.38:1	80	20	16
c.	247,1	75	60	10	17	15	23	1.44:1	1.56:1	(35)		
d.	247,80	75	60	10	17	15	23	1.44:1	1.36:1	80	16	12
e.	255,1	65	52	10	16	25	32	1.46:1	1.54:1	(35)		
f.	255,80	65	52	10	16	25	32	1.36:1	1.36:1	80	15	15
g.	257,1	45	36	10	14	45	50	1.54:1	1.50:1	(35)		
h.	257,80	45	36	10	14	45	50	1.34:1	1.44:1	80	18	21
i.	258,1 4 PLY	45	36	10	14	45	50	1.60:1	1.60:1	(35)		
j.	258,80 4 PLY	45	36	10	14	45	50	1.42:1	1.44:1	80	18	16
k.	255,13 45° GRAY	65	52	10	16	25	32	1.64:1	1.64:1	(35)		
l.	255,803 45° GRAY	65	52	10	16	25	32	1.46:1	1.40:1	80	18	16
m.	255,50	65	52	10	16	25	32	1.60:1	1.50:1	50	8	9.6
n.	255,60	65	52	10	16	25	32	1.56:1	1.46:1	60	12	11
o.	255,70	65	52	10	16	25	32	1.40:1	1.40:1	70	15	14.6
p.	179,1 WITH LLDPE	80	64	0	8	LLDPE 20	28	1.56:1	1.50:1	(35)		
q.	179,80 WITH LLDPE	80	64	0	8	LLDPE 20	28	1.40:1	1.40:1	80	15	12.5
r.	255,802	65	52	10	16	25	32	ca. 1.40:1	ca. 1.40:1	80	ca. 16	ca. 3

TABLE 1 (continued)

WEIGHT	YIELD POINT IN NEWTON		ENERGY AT BREAK. NEWTON·M.		ULTIMATE TENSILE STRENGTH IN NEWTON		ELONGATION AT BREAK. %	
	g/sq.m	P.D.	C.D.	P.D.	C.D.	P.D.	C.D.	P.D.
71	27	12	14.9	8.9	89	67	554	421
82	36	26	15.9	10.1	85	55	563	538
76	34	14	17.8	10.9	98	71	596	507
87	36	26	18.0	13.5	87	63	637	641
80	32	12	21.0	7.3	104	54	706	410
98	39	28	17.9	14.7	84	65	636	680
74	27	14	15.8	8.5	83	57	585	467
89	26	27	13.3	7.3	52	50	450	391
86	39	19	23.1	12.7	125	80	658	497
120	42	33	26.1	14.1	114	78	756	533
67	29	9	12.2	6.0	80	49	502	392
88	33	25	20.5	12.2	86	61	780	588
75	31	16	14.5	8.0	81	51	577	470
79	31	19	19.9	9.9	98	54	699	543
92	33	23	18.2	10.6	83	53	703	538
83	40	20	19.8	11.8	120	86	541	422
100	49	38	14.8	12.3	95	77	439	448
CA. 100	33	32	18.0	10.7	77	62	744	478

The layer for improved heat sealing consists of 70% "Hostalen 1022" and 30% "Nordel 1500".

The layer for improved lamination consists of 50% "Hostalen 1022" and 50% "Nordel 1500".

5 The extrusion temperature is 250°C and the blow ratio 1:1.

Each of the tubular films is cut helically under an angle of 30° and two such films, each having a width of about 20 cm, are laminated and stretched with the layers for improved lamination facing one another. Initially, the lamination and simultaneous transverse stretching are effected by passing the films six or seven times through the nip between a set of grooved rollers of the type shown in British patent specification No. 1.526.722, Fig. 7. The division on each roller is 1.8 mm, the width of each tip is 0.4 mm and the tip is circularly rounded. The intermeshing between the tips is 0.9 mm. The stretching is carried out at 35°C .

Subsequently, each sample is stretched longitudinally at the same temperature by means of rollers.

Stretch ratios are determined by printed marks.

20 During the longitudinal stretching, the width is reduced significantly.

Those samples (as will be described below) which are subjected to heat treatment are over-stretched in the longitudinal direction and finally further stretched in the transverse direction. The aim is that the heat treated samples should end at the same stretch ratios and square meter weight as those which are not heat treated. The pleated configuration created by this last transverse stretching is maintained in the film.

30 Heat treatment is then carried out at various temperatures on 60 cm long and 10 cm wide specimens which are carried forward and backward over a reciprocating heated roller during a period of 120 sec. and under a tension of 300 g. Different temperatures are tried. The specimens are brought in contact with the roller while they still have the pleated configuration but the pleats gradually disappear while the material shrinks.

35 Samples k and l deviate from the above by being cut under an angle of 45° instead of 30° .

Samples i and j deviate in being 4-layered. The angles are as follows: $+45^{\circ}$, $+30^{\circ}$, -30° , -45° .

Samples p and q deviate by also being 4-layered materials,

with the same directions and further by the composition of the main layer, which is:

80% "Hostalen 1022"

5 20% linear low density polyethylene of melt index 1.0 and a density of 0.92.

The melt index is measured according to ASTM D 1238 condition L except that the temperature is 190°C,

10 Sample r is a 2-ply sample similar to sample f regarding composition, angles and heat-treatment temperature, but deviates by not being subjected to the last transverse stretching and therefore not being in a pleated configuration when it is brought in contact with the hot roller. It is heat treated without any essential transverse
15 contraction, but with longitudinal contraction similar to sample f.

15 mm samples are cut in the machine and cross machine directions of each sample.

Stress-strain diagrams are taken at a velocity of 15 cm per minute and an initial distance of 50 mm between the clamps.

20 The results obtained will appear from the table and from the diagrams in Figures 2 and 3. The diagrams in Fig. 2 compare samples e, f, m and o which all have the same composition and which are treated in the same manner, except that the annealing temperature varies.

25 The diagrams in Fig. 3 compare samples b, d, f and h which contain different percentages of polyethylene, but otherwise are identical, the annealing temperature of this series being 80°C. In the diagrams of Figures 1 and 2 the values of force and energy are corrected to a gauge of 80 g/m².

30 As regards the comparison between the sample r which, in essence, was not allowed to shrink transversely, and the similar sample f, which was allowed a significant shrinkage, the table shows that the shrunk film has essentially higher transverse elongation at break and transverse energy absorption, while the two samples have
35 about the same yield point in the transverse direction.

EXAMPLE 2

The procedure described in example 1 is carried out on a number of film compositions, described in table 2 below, however with the last transverse stretching step and the subsequent heat-treatment

taking place in continuous manner on a pilot machine. During this stretching step, the intermeshing of the grooved rollers with each other is adjusted to obtain such a degree of pleating that there will be practically no transverse tension in the film during the heat treatment, but also so that all pleats produced by this stretching disappear due to the transverse shrinkage.

The extrusion temperature is in all cases 200°C with a blow ratio of 1:1 and a moderate air cooling.

The high-strength laminate are in all cases made from two spirally cut extruded tubular films. Different angles of cutting have been tried, see table 2.

All steps of stretching are carried out at 35°C , and the heat treatment is effected on a roller heated to 80°C . The heat treatment takes about 10 seconds. The laminate is held practically tension-free while being fed in between the last pair of grooved rollers (those which immediately precede the roller for heat treatment). This measure causes the laminate to shrink about 5-10% in the longitudinal direction during the transverse stretching between the grooved rollers. After this stretching, the laminate follows the surface of one of these rollers and is then directly transferred from this surface to the surface of the hot roller, the distance between these surfaces being only about 1 cm. This guided transfer secures that the fine pleats, produced by the stretching between the grooved rollers, remain fine and even so as to cause an even transverse contraction on the hot roller.

The latter is driven at a circumferential velocity which is about 10% lower than the circumferential velocity of the last set of grooved rollers. This measure, and a minimum tension at the take-off from the hot roller, gives the laminate a high freedom to shrink longitudinally.

When leaving the hot roller, the laminate is transferred to a cooling roller, after which it is wound up.

The longitudinal and transverse stretch ratios are measured after each step of the process by measuring the deformation of circles, which have been printed on the film before the first stretching step. The aim is a final stretch ratio (i.e. after the heat treatment) of 1.40:1 in both directions.

The adjustment of the transverse ratio takes place by the number of transverse stretching steps, which have been varied be-

tween 5 and 7 (to which comes the last one before the heat treatment). The adjustment of the longitudinal stretch ratio takes place by variation of the relative velocities of the rollers in the unit for longitudinal stretching. A proper adjustment of the stretch ratios is a complicated matter, and variations between 1.35:1 and 1.45:1 have been tolerated.

The different laminates thus produced are tested for:

- a) Elmendorf Tear Propagation Resistance according to BS 308 B (43 mm tear),
- b) Beach Puncture Resistance according to BS 4816:72;
- c) Falling Dart Impact Strength according to ASTM 1709.

Description of the raw materials:

The melt flow index (m.f.i.) refers to ASTM D 1238 condition L (in case of polypropylenes) or condition E (in the case of polyethylenes or EPDM).

- | | |
|-------------------|---|
| "Dowlex 2045": | LLDPE of density 0,920 and m.f.i. = 1.0 |
| "Hostalen 9255": | HMIHDPE of density about 0,95 and m.f.i. = about 0.05. |
| "Hostalen 1050": | homo-PP of m.f.i. = 0.4. |
| "Hostalen 1022": | co-PP of m.f.i. = 0.4 (further description see example 1). |
| "Novolen 1300 E": | gas phase-polymerized PP with about 20% contents of atactic PP, partly forming a block-copolymer with the isotactic PP. |
| "Nordel 1500": | EPDM of m.f.i. = about 0.3. |
| EVA: | An EVA containing about 20% vinylacetate and of m.f.i. = about 5. |

TABLE 2

Film Code No.	Composition					Direction of ply degrees	Film weight g/sq m	Falling Dart Impact Strength grams	Elmendorf tear Strength (43 mm.tear)			Beach Puncture Resistance, Joules	
	Inner layer (for improved lamination), 10% of total	Middle layer 75% of total	Outer layer (for sealing), 15% of total	MD	CD				45°	MD	CD		
R402	70% "Dovlex 2045" 30% "Nordel 1500"	80% "Hostalen 1022" 20% "Dovlex 2045"	100% "Dovlex 2045"	30	75	500-800	2160*	1070	1340	11.0	9.4		
R404		80% "Novolen 1300 E" 20% "Dovlex 2045"	"	45	75	600-800	1480	1100	920	14.2	13.3		
		35% "Hostalen 9255" 35% "Hostalen 1022"	"	30	71	600-700	2910*	1450	1770*	6.4	9.1		
R407	"	30% "Dovlex 2045"	"	45	74	600-800	2790*	1830	1280	9.9	13.8		
		50% "Hostalen 1022"	"	30	78	400-700	1620	1870	2400*	11.1	7.0		
		20% "Hostalen 1022"	70% "Hostalen 1022"	45	85	400-600	3030*	2110	2270*	7.9	7.5		
R414	"	20% "Hostalen 9255"	30% "Nordel 1500"	30	79	600-900	1410	1430	2210	13.7	11.9		
		20% "Dovlex 2045"	"	45	73	600-800	1460	1400	990	11.9	12.4		
		10% "Nordel 1500"	"	60	71	600-800	1660	2750*	1050	10.3 (average of MD and CD)			
R417	"	50% "Novolen 1300 E" 20% "Hostalen 1022"	"	30	77	600-900	1280	1250	2040*	11.9	12.6		
		20% "Dovlex 2045"	"	45	82	800-900	1990	1460	750	13.3	14.0		
		10% "Nordel 1500"	"	60	80	800-900	1780	2490*	650	12.1	13.6		
R419	"	50% "Hostalen 1050" 20% "Hostalen 9255"	"	30	74	500-700	1670	1520	2050	10.2	8.5		
		20% "Dovlex 2045"	"	45	71	500-800	2020	1120	1360	11.3	10.5		
R420	"	10% "Nordel 1500"	100% "Dovlex 2045"	45	75	500-800	2450	1620	1850	8.7	7.4		
R421	"	20% "Hostalen 1022" 20% "Hostalen 9255"	"	45	77	700-900	500	2190*	800	12.9	9.9		
		20% "EVA"	"										
R422	"	50% "Hostalen 1022" 20% "Hostalen 9255"	"	45	84	700-900	2460*	1420	2160*	13.6	10.2		
		20% "Dovlex 2045"	"										
		10% "Nordel 1500"	"										
Low density polyethylene (200 µm) Ordinary sack quality film for comparison					184	500-600	840	1300	1700	5.0 (average of MD and CD)			

* = higher than, and indicates that one or more of the single tests exceeded the maximum of the apparatus.

Several of the samples were further tested for Elmendorf Tear Propagation Strength at -15°C . For the samples of composition R 407, R 414 and R 419, this gave the same results (within the ranges of accuracy of this method) as the test results at 20°C shown in table 2. This high performance at low temperatures is surprising in view of the high contents of polypropylene, but explicable by the microstructure, which comprises the microscopical to submicroscopical fibrils of stiff polypropylene which are almost entirely embedded in relatively soft polyethylene.

A study of the tear resistance values in relation to the lamination angles (see table 2) gives the result that the 45° laminates show a significant weakness (relatively speaking) in their 45° directions, i.e. parallel to the direction of grain in one of the layers.

The same is not true for the 30° laminates, which generally show significantly higher all-over tear values, considering that the weakest direction generally determines the value of the laminate with respect to tear propagation resistance.

An exception to the rule that the 45° laminates exhibit a relatively low tear propagation resistance along the 45° direction, is found in the composition R 407. The main layer (middle layer) of this composition consists of HMHDPE and LLDPE in combination with a PP of significantly lower molecular weight than the HMHDPE, cf. claim 18. It is believed that the improved 45° tear strength in this case is due to the advantageous effects explained in the general description in connection with this claim.

Finally, the compositions containing 100% LLDPE in the layers for sealing (i.e. R 402, 404, 407, 420, 421, 422) have been found to form an adequate seal by ultrasonic sealing. The seal resists shear forces up to about 5-6 kp/2.5 mm and peel forces up to about 2 kp/2.5 mm. In this connection it is of importance that the seal layer and the matrix in the middle layer consist of essentially the same material, namely both of a low-density polyethylene type, while the fibrillar, discontinuous, embedded phase of the middle layer consists of the much higher melting polypropylene.

EXAMPLE 3

High-strength laminates were produced from two compositions, both entirely consisting of HMHDPE and LLDPE, except for minor amounts of EPDM in the layer for improved lamination. The procedure was identical to that explained in example 2, except that a

prototype machine for full technical scale operation was used.

5 In both cases, the extrusion temperature was 240°C , the angle of cutting 45° , the temperature of stretching 35°C , the temperature of the rollers for heat treatment 80°C , the time of heat treatment about 10 sec. Two heated rollers were used, one after the other, and subsequently two cooling rollers. The final stretch ratio, measured after heat treatment, was about 1.4:1 in both directions.

10 The entire stretching/lamination process including the heat treatment was operated in-line, the line comprising five transverse stretching stations, one longitudinal stretching station, and the last stretching station supplying the laminate with pleats for the "free-shrinkage" heat treatment. Between the last pair of grooved rollers and the first roller for heat treatment, and in close proximity to both, was an idle roller serving to keep the pleats fine and even.

15 The transverse stretching ratio was controlled by adjustment of the intermeshing between the grooved rollers in each of the first five pairs of grooved rollers.

20 As in example 2, the intermeshing between the last pair of grooved rollers was adjusted to minimize the transverse tension during the heat treatment.

The lineary velocity of the laminate at the exit from the stretching/lamination line was about 30 m/min.

The composition of the films and the results of the laboratory testing appear from table 3.

25 The polymer designations and the test methods for impact, tear and puncture resistance are explained in example 2 above. The other mechanical properties were determined from strain/stress curves taken for 15 mm wide specimens, the initial distance between the draw-clamps being 50 mm.

30 Strain/stress curves were taken as a modestly low velocity, namely 150 mm/min. and at a very low velocity, namely 15 mm/min. The latter was tried in order to study the creep strength.

35 The yield tension (in Newton/mm^2) therefore was determined at each of the two velocities, while elongation at break (in %) and ultimate tensile tension (in Newton/mm^2) were determined only at the velocity 150 mm/min.

The laminate prepared from composition R 1 was further converted to open-mouth sacks on commercial sack-making machinery. It was first folded to a flat tube while being side-seamed by use of a

commercial hot-melt adhesive, then cut into lengths while being heat-sealed transversely to form the bottom of the sack. This seam was made by simple impulse sealing (without any kind of folding or over-taping) but with the conditions of sealing optimized to allow maximum shrinkage in the longitudinal direction. The dimension of the sack was about 100 cm x 50 cm. About 30 of such sacks were filled, closed by overtaping and drop-tested at minus 20°C in competition with sacks of similar size made from a 185 g/sq m low density polyethylene film of standard quality for sack production. By these tests the high-strength laminate was found to be clearly superior in spite of its much lower gauge. The weight of the high-strength laminate used for these bag tests was 80 g/sq m, in other words almost 2½ times as light as the ordinary polyethylene sack material.

TABLE 3

Film Code (for im- proved la- mination) No.	Composition			Film weight g/sq m	Elmendorf Tear Strength (43 mm tear)		Beach Puncture Resistance, Joules		Yield point tension N/mm ²		Ultimate Tensile Tension N/mm ²		Elongation at break %								
	Inner layer (for im- proved la- mination) 102 of to- tal	Middle layer 75% of total	Outer lay- er (for improved sealing) 15% of to- tal		ND	CD	ND	CD	ND	CD	ND	CD	ND	CD							
R1	70% "Dow- lex 2045" 50% "Ho- stalen 9255" 30% "Nor- del 1500"	50% "Ho- stalen 9255" 50% "Dow- lex 2045"	100% "Dow- lex 2045"	74	2020	2360	1350	10,4	13,1	12,2	150 mm/mm/ min.	150 mm/mm/ min.	19,5	19,3	20,3	51,8	43,9	30,0	603	536	408
R2	"	70% "Ho- stalen 9255" 30% "Dow- lex 2045"	"	73	3200	3000	2220+	4,5	6,3	6,7	150 mm/mm/ min.	150 mm/mm/ min.	20,3	19,7	21,6	49,7	48,5	26,9	536	540	324

* = higher than, and indicates that one or more of the single tests exceeded the maximum of the apparatus.

C l a i m s

1. A method of preparing a high strength sheet material comprising forming a laminate comprising at least two layers of a thermoplastic polymer material, each layer having a fibrillar grain structure providing a predominant direction of splittability in each said layer, the layers being bonded to one another with the said predominant directions of splittability transverse to each other, and biaxially orienting the molecules of said layers by stretching the layers in substantially uniaxial steps, the transverse stretching being effected by applying pressure to the surface of the laminate along lines extending substantially in the longitudinal direction of the laminate to impart thereto a waved configuration, c h a r a c t e r - i z e d in subjecting the biaxially oriented laminate to a heat treatment while allowing at least 7% shrinkage of the laminate to take place in at least its transverse direction.

2. A method as in claim 1, c h a r a c t e r i z e d in effecting the heat treatment by contacting a longitudinally pleated laminate with the surface of a hot body.

3. A method as in claim 2, c h a r a c t e r i z e d in that said heated body is a hot roller.

4. A method as in claim 2, c h a r a c t e r i z e d in introducing onto the heated body a laminate having the configuration obtained during the last transverse stretching step.

5. A method according to claim 4, c h a r a c t e r i z e d in allowing the laminate to contract longitudinally during said last transverse stretching step.

6. A method as in claim 3, c h a r a c t e r i z e d in that air bubbles entrapped between the laminate and the surface of the hot roller are removed by squeezing while allowing the laminate to slide along the surface of the hot roller.

7. A method as in claim 6, c h a r a c t e r i z e d in subjecting the laminate to vibrations comprising short intervals during which the laminate is forced against the surface of the hot roller.

8. A method of preparing a high strength sheet material comprising forming a laminate comprising at least two layers of a thermoplastic polymer material, each layer having a fibrillar grain structure providing a predominant direction of splittability in each of said layers, the layers being bonded to one another with the said predominant directions of splittability transverse to each other, and

biaxially orienting the molecules of said layers by stretching the layers in substantially uniaxial steps, wherein the thermoplastic polymer material consists of a blend of 40-85% by weight of polypropylene and 60-15% by weight of a lower melting or amorphous admixture which a) mainly consists of polyethylene incl. copolymers hereof, b) exhibits substantially the same or a higher elongation at break than the said polypropylene when tested at room temperature under slow stretching, c) has a modulus of elasticity which at room temperature is equal to or lower than that of a blend of 90% polyethylene of a density of 0.95 and 10% EPR containing 25% ethylene and 75% propylene, and wherein at least the last 25% of the biaxial stretching, measured on the area increase, is carried out below 50°C, characterized by the subsequent step of heat treating the biaxially oriented laminate at a temperature higher than 50°C, preferably at least 70°C.

9. A method according to claim 8, characterized by allowing the sheet to shrink at least 7% in at least one direction.

10. A method as in claim 8, characterized in that the stretch ratio in any direction and determined after shrinkage does not exceed 2.5:1.

11. A method as in claim 8, characterized in that the admixture comprises as its major component linear polyethylene.

12. A method as in claim 11, characterized in that the linear polyethylene is high density polyethylene of a melt flow index according to ASTM D 1238 condition E not exceeding 0.2 and that the admixture further comprises between 10 and 50% of a softening component, preferably an elastomer.

13. A method as in claim 8, characterized in that the linear polyethylene is linear low density polyethylene.

14. A method as in claim 13, characterized in that the melt flow index of said linear low density polyethylene according to ASTM D 1238 condition E does not exceed 3.

15. A method according to claim 8, characterized by selecting the polyethylene so that its shrinkability at 100°C, in the oriented state, is higher than the corresponding shrinkability of the polypropylene.

16. A method according to claim 8, characterized by admixing, as an alloying agent between the polypropylene

and the polyethylene, minor amounts of a branched polypropylene, e.g. a copolymer of propylene and a polyolefin with 4 or more carbon atoms.

5 17. A method of preparing a high strength sheet material comprising forming a laminate comprising at least two layers of a thermoplastic polymer material, each layer having a fibrillar grain providing a predominant direction of splittability in each said layer, the layers being bonded to one another with the said predominant
10 directions of splittability transverse to each other, and biaxially orienting the molecules of said layers by stretching the layers in substantially uniaxial steps, c h a r a c t e r i z e d in that the direction of splittability in each layer of said layers of the laminate to be biaxially oriented forms an angle of between 10 and 35° with the machine direction of the laminate.

15 18. A method as in claim 17, c h a r a c t e r i z e d in that the stretch ratio in any direction and determined after shrinkage does not exceed 2.5:1.

 19. A method of preparing a high strength sheet material comprising forming a laminate comprising at least two layers of a
20 thermoplastic polymer blend comprising polyethylene, each layer having a fibrillar grain structure providing a predominant direction of splittability in each said layer, the layers being bonded to one another with the said predominant directions of splittability transverse to each other, and biaxially orienting the molecules of said layers by
25 stretching the layers in substantially uniaxial steps to convert the grain of polymer into a zig-zagging micropattern, c h a r a c t e r i z e d by said blend is composed of high molecular weight high density polyethylene and low density polyethylene having a significantly lower molecular weight, said low density polyethylene being
30 selected from the group of copolymers and/or branched polyethylenes which a) exhibit substantially the same or higher elongation at break than the said high molecular weight high density polyethylene when tested at room temperature under slow stretching, b) are capable of distinctly segregating, while forming a distinct microphase, from said
35 high molecular weight high density polyethylene on cooling of a molten homogeneous blend of the said components.

 20. A method according to claim 20, c h a r a c t e r i z e d in that said blend further contains polypropylene of a molecular weight significantly lower than that of said high molecular

weight high density polyethylene.

21. A method according to claim 21, c h a r a c t e r i -
z e d in that said blend further contains minor amounts of an alloy-
ing agent, e.g. a copolymer of propylene and a polyolefin with 4 or
5 more carbon atoms.

22. A method according to claim 20 and/or 21, c h a r a c -
t e r i z e d by allowing the sheet to shrink at least 7% in at least
one direction.

23. A method according to claim 20 and/or 21, c h a r a c -
10 t e r i z e d in that the stretch ratio in any direction and determi-
ned after shrinkage does not exceed 2.5:1.

24. A method of preparing a high strength sheet material
comprising forming a laminate from at least two separately extruded
films of thermoplastic polymer material, each film having a) a main
15 layer exhibiting a fibrillar grain structure providing a predominant
direction of splittability in each said film, and b) a second layer for
controlling bonding strength, the films being bonded to one another
with the said predominant directions of splittability transverse to each
other, the second layer of one film facing the second layer of the
20 other film, and biaxially orienting the molecules of said layers by
stretching the layers in substantially uniaxial steps, the transverse
stretching and the bonding being effected by applying pressure to
the surface of the laminate along lines extending substantially in the
longitudinal direction of the laminate to impart thereto a waved confi-
25 guration, and in which main layers the fibrillar grain structure con-
sists of highly crystalline polypropylene and/or high density polyethy-
lene micro fibrils which are generally embedded in a matrix material
predominantly consisting of low density polyethylene, c h a r a c -
t e r i z e d in a) that said matrix material exhibits an elongation at
30 break similar to or higher than that of the fibrilforming polypropylene
or high density polyethylene when tested at room temperature under
slow stretch, b) that said second layers mainly consist of branched p
olyethylene and exhibit a heat-seal temperature higher than 100°C and
an elongation at break similar to or higher than that of the fibril-
35 forming polypropylene or high density polyethylene.

25. A method according to claim 25, c h a r a c t e r i -
z e d by heat treating the laminate below the temperature at which
the second layers heat-seal to each other.

26. A method according to claim 26, c h a r a c t e r i z -

ed in that said matrix material has a melting range lower than that of said second layer and the laminate is allowed to shrink, at least in one direction, during said heat treatment.

27. An apparatus for carrying out the method according to claim 1, comprising means for preparing a laminate and means for stretching said laminate in substantially uniaxial steps, the means for transversely stretching the laminate comprising means for applying pressure to the surface of the laminate along lines extending substantially in the longitudinal direction of the laminate to impart thereto a waved configuration, characterized in that it further comprises means for heat treating the biaxially oriented laminate while allowing a shrinkage of the laminate to take place in at least its transverse direction.

28. An apparatus as in claim 28, characterized in that said heat treating means comprise at least one heated roller and that it further comprises means for introducing a longitudinally pleated laminate onto said heated roller.

29. An apparatus as in claim 29, wherein the means for transversely stretching the laminate comprise at least one pair of intermeshing grooved roller, characterized in that said heated roller is placed in close proximity of the surface of one of the roller of said pair of intermeshing grooved rollers to allow the laminate to be contacted with the surface of said heated roller immediately after having left the surface of said roller of the pair of intermeshing grooved rollers.

30. An apparatus as in claim 29, wherein the means for transversely stretching the laminate comprise at least one pair of intermeshing grooved rollers, characterized in one or more conveyor rollers are arranged between the last pair of intermeshing grooved rollers and the said heated roller, the adjacent rollers in said assembly being in so close proximity to one another that the film is supported by a roller surface during substantially all of its travel from the last pair of grooved rollers to the heated roller.

31. An apparatus as in claim 28, characterized in that it additionally comprises a counter roller located adjacent to the hot roller and cooperating with said hot roller to remove air bubbles entrapped between the laminate and the surface of the hot roller by squeezing while allowing the laminate to slide along the surface of the hot roller.

32. An apparatus as in claim 32, characterized in that it also comprises means for vibrating said counter roller relative to said hot roller.

5

10

15

20

25

30

35




FIG.1

0090380




FIG. 2




FIG. 3



European Patent
Office

EUROPEAN SEARCH REPORT

0090380

Application number

EP 83 10 3001

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 3)
D, Y	GB-A-1 526 722 (OLE-BENDT RASMUSSEN) * Page 2, lines 77-100 *	1	B 29 D 7/24 B 32 B 27/08
Y	GB-A-1 169 661 (HERCULES INC.) * Claim 1; page 3, lines 32-48 *	1	
D, A	GB-A-1 526 724 (OLE-BENDT RASMUSSEN)		
A	GB-A-1 171 971 (ICI)		
			TECHNICAL FIELDS SEARCHED (Int. Cl. 3)
			B 32 B B 29 D 7/24
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 14-07-1983	Examiner VAN THIELEN J.B.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			
T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			